

## PROXIMA

Basis Weight		Thickness		Stiffness (Taber 15°)	
g/m <sup>2</sup>	24"x36"			mN·m (±10%)	
±3%	500 (lb)	µm (±4%)	pt (±4%)	CD	MD
215	132	345	13.6	4.6	9.4
235	144	370	14.6	6.4	12.7
250	154	405	15.9	7.6	15.7
270	166	445	17.5	9.5	19.1
295	181	495	19.5	12.3	24.9
325	200	545	21.5	15.2	30.8
360	221	615	24.2	20.9	42.8

Property	Unit	Value
PPS (Top)	µm	1.4
Moisture	%	6.5 ±1.0
Brightness (Top)	%	93.0±2.0
75°Gloss(Top)	%	45±5
IGT Blister(Top)	m/s	≥1.5
COBB Test(60s) (Top & Bottom)	g/m <sup>2</sup>	40±15
PLY Bonding	J/m <sup>2</sup>	≥130
SQUARENESS	mm	≤2
SIZE DEVIATION/ UNEVEN END FACE	mm	0-2

Test condition (ISO): temp 23±1°C, relative humidity 50±2%