

Eska Duo

Description	Standard	Unit	Values		
Weight	ISO 536	gsm (g/m ²)	675	850	1000
Thickness	ISO 534	microns (µm)	1000	1250	1500
Dynamic Stiffness MD	ISO 5629	mNm	330	665	980
Dynamic Stiffness CD	ISO 5629	mNm	180	345	530
Bursting Strength (top side)	ISO 2759	kPa	820	880	865
Bursting Strength (reverse side)	ISO 2759	kPa	860	875	890
COBB 60	ISO 535	g/m ² /60 sec	100		
Moisture	ISO 287	%	8.0		

FSC® certified