

MetsaBoard Classic

Description	Standard	Unit	Values									
			200	210	225	235	250	260	275	290	315	340
Weight	ISO 536	gsm (g/m ²)	200	210	225	235	250	260	275	290	315	340
Thickness	ISO 534	microns (µm)	350	375	400	425	450	475	500	550	600	650
Bending Stiffness Taber 15° MD	ISO 2493	mNm	4.7	5.8	7.0	8.4	9.7	11.0	12.6	15.8	18.9	22.1
Bending Stiffness Taber 15° CD	ISO 2493	mNm	10.5	12.1	15.0	17.0	19.2	22.6	25.2	31.0	37.8	45.2
Moisture Content	ISO 287	%	8.0				8.5				9.0	
Smoothness PPS10 (top side)	ISO 8791.4	µm	1.4									
Brightness Illumination C/2° (top side)	ISO 2470-1	%	84									
Gloss Hunter 75°	T-480	%	35									
Off-flavour (Robinson test) 12m in original packaging	EN 1230-2		<1									