

## Topliner

Data sheet	Specification	Unit	Technical detail					
Substance	ISO 536	gsm (g/m <sup>2</sup> )	160	180	195	210	230	250
Thickness	EN 20534	microns (µm)	180	200	220	240	260	280
Burst Strength	ISO 2759	kPa	330	380	395	410	430	450
SCT cd	ISO 9895	kN/m	2.3	2.7	2.8	3.0	3.2	3.4
Smoothness PPS (top side)	ISO 8791-4	µm	1.5					
Gloss 75°	ISO 8254	%	50					
Brightness (top side)	ISO 2470-2	%	83					

ISO 9001  
 ISO 50001  
 EN 15593