

## Cyber Premium

Description	Standard	Unit	Values								
Weight	T-410	gsm (g/m <sup>2</sup> )	210	240	260	270	280	300	330	360	380
Thickness	T-411	microns (µm)	346	398	437	470	490	532	592	648	684
Stiffness Taber 15° MD	T-489	mNm	7.7	12.7	16.7	19.2	21.8	26.6	33.2	43.2	48.9
Stiffness Taber 15° CD	T-489	mNm	3.8	6.3	8.4	9.6	10.9	13.3	16.6	21.6	24.4
Ply Bond (avg.)	T-569	J/m <sup>2</sup>	150								
Roughness PPS (top side)	T-555	µm	2.1		2.3				2.5		
Brightness ISO (top side)	T-452	%	85 min								
Whiteness CIE (top side)	T-560	%	85 min								
Surface Strength IGT Pick (top side)	ISO 3782 & ISO 3783	m/sec	0.7 min								
Gloss 75° (top side)	T-480	%	35								
Moisture	T-412	%	6.0-7.5						7.0-8.5		

**FSC® certified**