

## Cyber XL Pac

Description	Standard	Unit	Values							
			220	260	280	300	340	370	400	
Weight	T-410	gsm (g/m <sup>2</sup> )	220	260	280	300	340	370	400	
Thickness	T-411	microns (µm)	341	403	448	480	544	592	640	
Stiffness Taber 15° MD	T-489	mNm	9.0	14.5	18.3	23.3	32.8	41.3	51.8	
Stiffness Taber 15° CD	T-489	mNm	5.0	7.5	9.0	11.0	15.7	19.2	26.1	
Ply Bond (avg.)	T-569	J/m <sup>2</sup>	150							
Roughness PPS (top side)	T-555	µm	1.5	1.8				2.0		
Brightness ISO (top side)	T-452	%	85 min							
Whiteness CIE (top side)	T-560	%	85 min							
Surface Strength IGT Pick	ISO 3782 & ISO 3783	m/sec	0.7 min							
Gloss 75° (top side)	T-480	%	30							
Moisture	T-412	%	7.0				8.0			

**FSC® certified**