

Excellent Top Kraft

Description	Standard	Unit	Values					
Weight	ISO 536	gsm (g/m ²)	230	245	270	300	330	370
Thickness	EN 20534	microns (µm)	380	410	455	525	580	650
Stiffness Taber 15° MD	DIN 53121	mNm	11.8	15.5	21.4	29.2	36.9	46.8
Stiffness Taber 15° CD	DIN 53121	mNm	5.4	7.1	9.2	12.6	15.9	20.2
GE Brightness (top side)	ISO 2470-2	%	88					
Smoothness PPS (top side)	ISO 8791-4	µm	0.8					
Gloss 75°	ISO 8254	%	55					
Cobb 60 sec	ISO 535	g/m ²	30					

FSC® certified

ISO 9001