

Invercote G

Description	Standard	Unit	Values											
			180	200	220	240	260	280	300	330	350	380		
Weight	ISO 536	gsm (g/m ²)	180	200	220	240	260	280	300	330	350	380		
Thickness	ISO 534	microns (µm)	205	235	260	300	330	360	395	435	465	505		
Bending Taber 15° MD	ISO 2493	mNm	3.1	4.6	6.8	9.2	11.8	15.2	19.6	26.5	31.4	39.6		
Bending Taber 15° CD	ISO 2493	mNm	1.4	2.2	3.1	4.0	5.2	6.6	8.7	11.1	13.3	16.7		
Opacity	ISO 2471	%	94.5	95.0	97.0	97.3	97.7	98.1	98.6	98.8	99.1	99.2		
Whiteness (printing side)	ISO 11475	%	129											
Whiteness (reverse)	ISO 11475	%	110					122						
Brightness (printing side)	ISO 2470	%	94											
Brightness (reverse)	ISO 2470	%	90					94						
Board Gloss 75°	ISO 8254-1	%	40											
Cobb 60	ISO 535	g/m ² /60 sec	30											

FSC® certified

ISO 9001
 ISO 14001
 OHSAS 18001
 ISO 50001