

MetsaBoard Pro FBB Bright

Description	Standard	Unit	Values										
			180	195	220	230	245	255	265	280	290	320	350
Weight	ISO 536	gsm (g/m ²)	180	195	220	230	245	255	265	280	290	320	350
Thickness	ISO 534	microns (µm)	260	305	355	385	415	435	455	485	505	555	610
Bending Stiffness Taber 15° MD	ISO 2493	mNm	2.4	3.8	5.4	6.6	8.1	9.0	10.0	11.6	13.0	16.0	19.0
Bending Stiffness Taber 15° CD	ISO 2493	mNm	5.2	7.8	11.0	13.5	16.5	18.4	20.2	23.3	26.3	32.5	38.0
Moisture Content	ISO 287	%	6.8	7.0		7.2		7.7		7.8	8.1	8.3	8.5
Smoothness PPS10 (top side)	ISO 8791.4	µm	1.0										
Brightness Illumination C/2° (top side)	ISO 2470-1	%	91										
Gloss Hunter 75°	T-480	%	48										
Off-flavour (Robinson test) 12m in original packaging	EN 1230-2		<1										