

Omnistar

Description	Standard	Unit	Values								
			205	230	240	250	260	270	285	310	340
Weight		gsm (g/m ²)	205	230	240	250	260	270	285	310	340
Thickness		microns (µm)	260	315	310	340	350	370	410	460	510
Stiffness Taber 15° MD		mNm	2.0	3.6	3.5	4.5	4.85	5.4	7.0	10.0	13.0
Stiffness Taber 15° CD		mNm	3.6	6.5	6.45	8.0	8.8	9.5	12.0	17.0	22.0
PPS (top/back)		µm	1.7/1.8								
Moisture		%	6.5								
Brightness		%	92								
75° Gloss (top/back)		%	45/50								
IGT Blister (top side)		m/s	1.2	1.5	1.2	1.5	1.2	1.5	1.5	1.5	1.5
IGT Blister (reverse side)		m/s	1.2	1.0	1.2	1.0	1.2	1.0	1.0	1.0	1.0
COBB 60 sec		g/m ²	35.0	40.0	35.0	40.0	35.0	40.0	40.0	40.0	40.0
Ply Bond		J/m ²	130								