

## PankaBrite

Description	Standard	Unit	Values											
			275	300	325	350	375	400	425	450	475	500	550	
Weight	ISO 536	gsm (g/m <sup>2</sup> )	275	300	325	350	375	400	425	450	475	500	550	
Thickness	ISO 534	microns (µm)	460	510	560	610	670	720	770	830	885	940	1030	
Bending Moment Taber 15° MD	ISO 2493	mNm	20.0	26.3	32.5	39.5	46.4	55.4	65.1	74.8	86.5	97.6	123.9	
Bending Moment Taber 15° CD	ISO 2493	mNm	8.8	12.1	14.9	17.9	21.1	25.2	29.5	33.9	39.1	44.1	55.9	
Moisture	ISO 287	%	8.5				9.0				9.5			
ISO Brightness C/2° (top side)	ISO 2470-1	%	85											
Colour CIELAB L* C/2° (top side)	ISO 5631-1		93.5											
Colour CIELAB a* C/2° (top side)	ISO 5631-1		0.7											
Colour CIELAB b* C/2° (top side)	ISO 5631-1		0.5											
Surface Smoothness PPS 10	ISO 8791-4	µm	1.0											
Gloss 75° (top side)	ISO 8254-1	%	40											
Scott Bond	T 569	J/m <sup>2</sup>	110											

ISO 9001  
ISO 14001  
ISO 22000