

PrintKote®

Description	Method	Unit	Values										
			240	265	280	295	305	325	345	375	405	435	460
Basis Weight	T-410	g/m ²	240	265	280	295	305	325	345	375	405	435	460
Thickness	T-411	mic	305	356	381	406	432	457	508	559	610	660	711
Stiffness Taber 15° MD	T-489	mNm	8.3	11.8	14.7	16.7	18.6	21.6	27.5	34.8	43.1	49.0	53.9
Stiffness Taber 15° CD	T-489	mNm	4.4	5.9	8.3	9.3	10.3	11.8	15.2	18.6	22.6	26.0	28.4
Moisture	T-412	%	5.3	5.3	5.5	5.6	5.5	5.6	5.6	5.6	5.6	5.6	5.6
Internal Bond	T-569	J/m ²	137	147	147	147	147	147	158	168	168	168	168
GE Brightness (coated side)	T-452	%	86										
Parker Print (coated side)	T-555	µm	1.0	1.0	1.1	1.1	1.2	1.1	1.2	1.2	1.2	1.2	1.2
ZDT	T-541	kPa	358	324	310	310	276	276	276	276	276	276	276

ISO 9001