

# Green Laser

	Standard	Unit	Target
Thickness	ISO 534	micron	96
Opacity	ISO 2471	%	92
CIE Whiteness	ISO 11475		136
Brightness D65	ISO 2470-2	%	101
Bendtsen Roughness	ISO 8791/2	ml/min	200
Stiffness MD	ISO 2493-1	mN	≥90
Stiffness CD	ISO 2493-1	mN	≥30
Tensile MD	ISO 1924-2	kN/m	≥4.5
Air Permeability	ISO 5636-3	m//min	≥1700
Moisture	ISO 287	%	4.0
Formation	Internal Method	#	≥25

